

GENERAL COATING SPECIFICATION FOR TUFAM® R66F

DESCRIPTION:	INFUSED POLYMER ANODIC COATING
COATING NAME:	TUFAM R66F
COATING HARDNESS:	42 – 50 Rc
COATING THICKNESS:	0.002 – 0.003” (includes anodic and polymer buildup)
TEMP OPERATING RANGE:	-360F TO 400F
EQUILIBRIUM WEAR RATES:	93 mg (mg/10,000 cycles ASTM D4060)
COEFFICIENT OF FRICTION:	0.096 Static 0.062 Kinetic (ASTM D1894)
FDA COMPLIANT:	YES

**Data based on average of multiple samples.
Results will vary and are application dependent.**

